

ALPHINE OIL LLC

CTR 11, PHASE 2, HAMRIYAH FREEZONE
AUTHORITY, SHARJAH - UAE

+971 6 579 8448

▶ +971 56 333 9927⋈ info@alphineoil.com

www.alphineoil.com

Product Specifications

BITUMEN MC 70

Cut Back Bitumen is an oil based substance.it is a semi-solid hydrocarbon product produced by removing the lighter fractions (such as liquid petroleum gas,petrol and diesel) from heavy crude oil during the refining process.

| Parameters | method | unit | Typical Result |
|--|------------|-------|----------------|
| Color | ASTM D1500 | - | BLACK |
| Viscosity @ 60 °C | ASTM D2170 | cSt | 70-140 |
| Flash Point | ASTM D93 | °C | 38 min |
| Water Content | ASTM D95 | % Vol | 0.2 max |
| Distillate, volume percent of total distillate to 360 oC | | | |
| To 225°C | | °C | 20 max |
| To 260°C | | °C | 20-60 |
| To 316°C | ASTM D402 | °C | 65-90 |
| Residue from distillation to 360°C | | °C | 55 min |
| Test on residue from distillation | | | |
| Viscosity @ 60 | ASTM D2170 | cSt | 100 |
| Penetration at 25°C | ASTM D5 | °C | 120-250 |
| Ductility at 25°C | ASTM D113 | °C | 100 min |
| Solubility in Trichloroethylene | ASTM D2042 | wt% | 99 min |